


[Log Out](#) [Order Form](#) [Work Files](#) [View Cart](#)[Browse Codes](#)[IP Listings](#)[Prior Art](#)[Derwent](#)[Advanced](#)[Boolean](#)[Quick/Number](#)[IP SEARCH](#)[HELP](#)

The Delphion  
Integrated  
View

**Other Views:**[INPADOC](#) | [Derwent...](#)**Title:** JP6254137A2: MULTILAYER PLASTIC BAG**Country:** JP Japan**Kind:** A**Inventor(s):** FUJII HITOSHI**Applicant/Assignee:** DAINIPPON PRINTING CO LTD  
[News, Profiles, Stocks and More about this company](#)**Issued/Filed Dates:** Sept. 13, 1994 / March 5, 1993**Application Number:** JP1993000069189**IPC Class:** A61J 1/10; B65D 65/40;**Priority Number(s):** March 5, 1993 JP1993000069189**Abstract:** **Purpose:** To improve heat resistance, shock resistance, barrier performance and sanitary efficiency by stacking using reaction type solventless adhesive resin at the time of laminating films for forming the respective layers in a multilayer plastic bag formed by a multilayer composite film.**Constitution:** A two-liquid reaction type solventless adhesive resin 2 is coated on nylon (3) 20µm thick at the coating temperature of 70°C by coating quantity of 2.0g/m2 to laminate polypropylene 50µm. Subsequently, for hardening the adhesive 2, aging at 40-45°C is performed for four days to manufacture a multilayer plastic sheet, and a bag is manufactured using the sheet. Thus, the change in a bag manufacturing stored liquid due to residual solvent is eliminated and heat resistance, shock resistance, barrier performance and sanitary efficiency can be improved.

COPYRIGHT: (C)1994,JPO&amp;Japio

**Family:** [Show known family members](#)**Other Abstract Info:** DERABS C94-329071 DERC94-329071**Foreign References:** No patents reference this one[Inquire Regarding Licensing](#)[Nominate this for the Gallery...](#)[View Image](#)

1 page